

PIEMONTE WHITE 7,5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A022838 7,5X15 7,40 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all requeriments

PHYSICAL PROPERTIES		
Water absorption capacity	EN ISO 10545-03	>10%
Flexion resistance	EN ISO 10545-04	$=> 20 \text{N/mm}^2$
Thermal shock resistance	EN ISO 10545-09	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Frost resistance	EN ISO 10545-12	Not pass the test

CHEMICAL PROPERTIES			
Resistance to acids	EN ISO 10545-13	GHA	
Resistance to alcalis	EN ISO 10545-13	GHA	
Resistance to cleaning products	EN ISO 10545-13	GA	
Resistance to chemical products in swimming pool water	EN ISO 10545-13	GA	
Stains resistance	EN ISO 10545-14	5	









MOLDURA PIEMONTE WHITE 5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023248 5X15 25,40 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









TORELLO PIEMONTE WHITE 2X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023236 2X15 13,60 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









PIEMONTE WHISPER SAGE 7,5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A022840 7,5X15 6,90 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all requeriments

PHYSICAL PROPERTIES		
Water absorption capacity	EN ISO 10545-03	>10%
Flexion resistance	EN ISO 10545-04	$=> 20 \text{N/mm}^2$
Thermal shock resistance	EN ISO 10545-09	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Frost resistance	EN ISO 10545-12	Not pass the test

CHEMICAL PROPERTIES			
Resistance to acids	EN ISO 10545-13	GHA	
Resistance to alcalis	EN ISO 10545-13	GHA	
Resistance to cleaning products	EN ISO 10545-13	GA	
Resistance to chemical products in swimming pool water	EN ISO 10545-13	GA	
Stains resistance	EN ISO 10545-14	5	










MOLDURA PIEMONTE WHISPER SAGE 5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023247 5X15 13,00 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









TORELLO PIEMONTE WHISPER SAGE 2X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023235 2X15 14,00 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









PIEMONTE CREAM 7,5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A022833 7,5X15 7,10 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality

UNE-EN 14411

It accomplished all requeriments

PHYSICAL PROPERTIES		
Water absorption capacity	EN ISO 10545-03	>10%
Flexion resistance	EN ISO 10545-04	$=> 20 \text{N/mm}^2$
Thermal shock resistance	EN ISO 10545-09	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Frost resistance	EN ISO 10545-12	Not pass the test

CHEMICAL PROPERTIES			
Resistance to acids	EN ISO 10545-13	GHA	
Resistance to alcalis	EN ISO 10545-13	GHA	
Resistance to cleaning products	EN ISO 10545-13	GA	
Resistance to chemical products in swimming pool water	EN ISO 10545-13	GA	
Stains resistance	EN ISO 10545-14	5	









MOLDURA PIEMONTE CREAM 5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023242 5X15 13,00 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









TORELLO PIEMONTE CREAM 2X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023230 2X15 14,00 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









PIEMONTE AVOCADO 7,5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A022835 7,5X15 6,90 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality

UNE-EN 14411

It accomplished all requeriments

PHYSICAL PROPERTIES		
Water absorption capacity	EN ISO 10545-03	>10%
Flexion resistance	EN ISO 10545-04	$=> 20 \text{N/mm}^2$
Thermal shock resistance	EN ISO 10545-09	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Frost resistance	EN ISO 10545-12	Not pass the test

CHEMICAL PROPERTIES			
Resistance to acids	EN ISO 10545-13	GHA	
Resistance to alcalis	EN ISO 10545-13	GHA	
Resistance to cleaning products	EN ISO 10545-13	GA	
Resistance to chemical products in swimming pool water	EN ISO 10545-13	GA	
Stains resistance	EN ISO 10545-14	5	









MOLDURA PIEMONTE AVOCADO

5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023238 5X15 13,00 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









TORELLO PIEMONTE AVOCADO

2X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023226 2X15 14,00 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









PIEMONTE APPLE 7,5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A022841 7,5X15 6,60 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality UNE-EN 14411 It accomplished all requeriments

PHYSICAL PROPERTIES		
Water absorption capacity	EN ISO 10545-03	>10%
Flexion resistance	EN ISO 10545-04	$=> 20 \text{N/mm}^2$
Thermal shock resistance	EN ISO 10545-09	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Frost resistance	EN ISO 10545-12	Not pass the test

CHEMICAL PROPERTIES			
Resistance to acids	EN ISO 10545-13	GHA	
Resistance to alcalis	EN ISO 10545-13	GHA	
Resistance to cleaning products	EN ISO 10545-13	GA	
Resistance to chemical products in swimming pool water	EN ISO 10545-13	GA	
Stains resistance	EN ISO 10545-14	5	









MOLDURA PIEMONTE APPLE 5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023237 5X15 13,00 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









TORELLO PIEMONTE APPLE 2X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023225 2X15 14,00 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test









PIEMONTE CEDAR 7,5X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A022839 7,5X15 6,90 REVESTI



DIMENSIONS AND SURFACE PROPERTIES

Size, thickness, side straightness, flatness, orthogonality

UNE-EN 14411

It accomplished all requeriments

PHYSICAL PROPERTIES		
Water absorption capacity	EN ISO 10545-03	>10%
Flexion resistance	EN ISO 10545-04	$=> 20 \text{N/mm}^2$
Thermal shock resistance	EN ISO 10545-09	It stands the test
Cracking resistance	EN ISO 10545-11	It stands the test
Frost resistance	EN ISO 10545-12	Not pass the test

CHEMICAL PROPERTIES			
Resistance to acids	EN ISO 10545-13	GHA	
Resistance to alcalis	EN ISO 10545-13	GHA	
Resistance to cleaning products	EN ISO 10545-13	GA	
Resistance to chemical products in swimming pool water	EN ISO 10545-13	GA	
Stains resistance	EN ISO 10545-14	5	









MOLDURA PIEMONTE CEDAR 5X15

GROUP REFERENCE THICKNESS (mm) SIZE (cm)

A023240 5X15 13,00 **REVESTI**



DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

EN ISO 10545-12 Frost resistance Not pass the test









TORELLO PIEMONTE CEDAR 2X15

REFERENCE SIZE (cm) THICKNESS (mm) GROUP

A023228 2X15 14,00 REVESTI

DIMENSIONS AND SURFACE PROPERTIES

PHYSICAL PROPERTIES

Frost resistance EN ISO 10545-12 Not pass the test



